

ARTICLE

Received 11 Oct 2014 | Accepted 10 Mar 2015 | Published 28 May 2015

DOI: 10.1038/ncomms7892

Predictive modelling-based design and experiments for synthesis and spinning of bioinspired silk fibres

Shangchao Lin^{1,2,*}, Seunghwa Ryu^{1,3,*}, Olena Tokareva^{1,4,*}, Greta Gronau^{1,5}, Matthew M. Jacobsen⁶, Wenwen Huang⁴, Daniel J. Rizzo⁷, David Li⁶, Cristian Staii⁷, Nicola M. Pugno^{8,9,10}, Joyce Y. Wong⁶, David L. Kaplan⁴ & Markus J. Buehler¹

Scalable computational modelling tools are required to guide the rational design of complex hierarchical materials with predictable functions. Here, we utilize mesoscopic modelling, integrated with genetic block copolymer synthesis and bioinspired spinning process, to demonstrate *de novo* materials design that incorporates chemistry, processing and material characterization. We find that intermediate hydrophobic/hydrophilic block ratios observed in natural spider silks and longer chain lengths lead to outstanding silk fibre formation. This design by nature is based on the optimal combination of protein solubility, self-assembled aggregate size and polymer network topology. The original homogeneous network structure becomes heterogeneous after spinning, enhancing the anisotropic network connectivity along the shear flow direction. Extending beyond the classical polymer theory, with insights from the percolation network model, we illustrate the direct proportionality between network conductance and fibre Young's modulus. This integrated approach provides a general path towards *de novo* functional network materials with enhanced mechanical properties and beyond (optical, electrical or thermal) as we have experimentally verified.

¹Laboratory for Atomistic and Molecular Mechanics (LAMM), Department of Civil and Environmental Engineering, Massachusetts Institute of Technology, Cambridge, Massachusetts 02139, USA. ² Department of Mechanical Engineering, Materials Science and Engineering Program, Florida State University, Tallahassee, Florida 32310, USA. ³ Department of Mechanical Engineering, Korea Advanced Institute of Science and Technology (KAIST), Daejeon 305-338, Korea. ⁴ Department of Biomedical Engineering, Tufts University, Medford, Massachusetts 02155, USA. ⁵ Institute for Particle Technology, Technische Universitat Braunschweig, Braunschweig 38104, Germany. ⁶ Department of Biomedical Engineering and Division of Materials Science and Engineering, Boston University, Boston, Massachusetts 02215, USA. ⁷ Department of Physics and Astronomy, Center for Nanoscopic Physics, Tufts University, Medford, Massachusetts 02155, USA. ⁸ Laboratory of Bio-Inspired and Graphene Nanomechanics, Department of Civil, Environmental and Mechanical Engineering, University of Trento, Via Mesiano 77, I-38123 Trento, Italy. ⁹ Centre for Materials and Microsystems, Fondazione Bruno Kessler, Via Sommarive 18, I-38123 Trento, Italy. ¹⁰ School of Engineering and Materials Science, Queen Mary University of London, Mile End Road, London E1 4NS, UK. * These authors contributed equally to this work. Correspondence and requests for materials should be addressed to M.J.B. (email: mbuehler@mit.edu).

ARTICLE

atural protein biomaterials such as silk have been the subject of intensive research due to the extraordinary properties with versatile potential applications^{1,2}. Among them, spider silks possess exceptional mechanical properties with toughness comparable to Kevlar³ and strength comparable to steel, yet by weight is six times lighter⁴. Silks, due to biocompatibility⁵ and biodegradability⁶, are useful proteinbased materials for biomedical applications such as wound sutures⁷, artificial nerve guides⁸, tissue regeneration^{9,10} and gene¹¹ or drug delivery¹². Despite the simple amino acid building blocks for silk proteins, spiders and silkworms produce silks with remarkable mechanical and adhesive properties by engineering nanoscale protein aggregate morphologies via multiple stages of spinning, relying at its foundation on selfassembly and shear flow-induced focusing along their microchannel-like spinning ducts. Silk protein sequence alterations, together with fibre-processing parameters, allow for a huge design space for new polymeric materials. The molecularlevel microstructure formation of polymer aggregates via selfassembly has been recognized as a very important process that determines the material properties. To fully harness these processes to generate defined material features, there have been extensive efforts^{13,14} to artificially synthesize the silk fibre with regenerative¹⁵ and synthetic (or recombinant)¹⁶⁻¹⁸ silks. Using recombinant silk is also more practical and cost effective than harvesting silk materials from spider farms and, therefore, has great potential for large-scale manufacturing. Yet, the design and implementation of synthetic imitations have been hindered by incomplete knowledge about the interplay between protein structure, fibre processing and fibre properties. These limitations have resulted in an inability to fully recapitulate the suite of remarkable mechanical properties of silk.

Synthetic silk protein sequences of this work contain three major building blocks named 'A' (poly(alanine) containing, hydrophobic domain), 'B' (GGX (X = R, L, Y or Q) rich, hydrophilic domain) and 'H' (hexahistidine fusion tag, introduced for facile purification, hydrophilic domain same as 'B'). 'A' and 'B' represent an abstraction of the natural silk protein sequence in which hydrophobic and hydrophilic domains are arranged repetitively into a multiblock copolymer. The aminoacid sequence in each domain is also identical to the native sequence in the major ampullate spidroin (MaSp1, Accession Number: P19837.3) of Nephila clavipes^{19,20}. Specifically, the sequences (Supplementary Table 1) for the 'A' and 'B' domains are GAGAAAAAGGAGTS and QGGYGGLGSQGSGRGGLGGQTS, respectively. For the 'A' domain, the hydrophobic alanine (A) amino acids are responsible for the self-assembly of proteins into aggregates via β -sheet stacking, whereas the glycine (G) amino acids facilitate the hydrogen bonding between β -sheets. As a result, the hydrophobic 'A' domains form stiff and strong β -sheet crystals, whereas the hydrophilic 'B' domains form disorganized and extensible amorphous regions. Theoretical models for describing the self-assembled morphologies of block copolymers are still limited to very simple copolymer structures²¹, in which Flory-Huggins parameters (χ_{AB}) are used to quantify the degree of incompatibility between the hydrophobic and the hydrophilic domains. For example, the self-consistent mean-field theory can only predict phase diagrams of pure diblock or triblock copolymers in bulk or with solvents²², but not the molecular structures in detail²³. On the other hand, our recent atomistic simulations revealed various structural details and mechanics of the crystalline and amorphous regions of the silk protein in aqueous environments $^{24-26}$. However, the atomistic simulations are not efficient enough to study the self-assembly process of a large number of proteins or polymers in the mesoscale. Therefore, scalable computational modelling approaches are required to

study more complicated protein-like multiblock copolymers, in particular, protein sequences with ~ 20 different amino-acid building blocks in aqueous environments.

With the above in mind, in this paper, we develop a coarsegrained description of silk proteins as multiblock copolymers based on the mesoscopic dissipative particle dynamics (DPD) simulation^{27,28} (see Methods), and apply the model to reveal the critical processing conditions and design parameters that control silk fibre assembly. We also validate the model against silk protein biosynthesis and characterization, and syringe needle fibre spinning and tensile testing (see Methods). This integrated modelling and experimental framework is illustrated in Fig. 1a. We reveal the structural evolution of the silk protein solution under shear flow and study how the 'A'-'B' domain ratio and the protein molecular weight (polymer chain length) affect the fibre formation process. Our simulation results and polymer network analysis suggest that intermediate 'A'-'B' domain ratio leads to homogeneous and well-connected polymer solution, which is the key during the fibre-spinning process. We also reveal that, in addition to the β -sheet crystal content, longer chains are crucial for the formation of robust fibres. The shear flow further enhances the alignment of longer polymers and the size of the β -sheet crystal, which leads to gelation and fibre assembly²⁹. Networks formed by shorter polymers are easily disrupted by the shear flow. To obtain a general polymer design principle, we extend beyond the classical polymer theory, which describes only homogeneous polymer aggregates before spinning with insights from the percolation network model, which also describes heterogeneous polymer networks after spinning. This molecular-level design principle for mechanically robust silk fibres is finally realized in our spinning and nanoindentation experiments.

Results

Effects of domain ratio and shear flow. To examine the effect of hydrophobic-hydrophilic ('A'-'B') domain ratios on fibre formation, three simple short peptide sequences with similar polymer chain length (molecular weight) are considered: HA₃B, H(AB)₂ and HAB₃ (Fig. 1b-d), with different domain ratios 3:1, 1:1 and 1:3, respectively. The 'A' domain is modelled using five hydrophobic 'a' beads and the 'B' domain is modelled using seven hydrophilic 'b' beads. DPD simulation results on the aqueous solutions of HAB₃, H(AB)₂ and HA₃B right after equilibration (before shear flow) is shown in Fig. 1b-d, middle panel. We expect that the electrostatic interactions between silk proteins will be relatively weak here, because the degree of protonation or deprotonation is quite low due to the use of organic solvents rather than water. Therefore, electrostatic interactions are currently neglected in the DPD model and such effect will be considered in future studies to better mimic the ionic aqueous environment in the natural spider silk-spinning process³⁰, in which the silk protein should be modelled as a polyelectrolyte. Starting with randomized polymer solutions, the equilibration of the system results in the formation of spherical polymer micelle structures in which hydrophobic 'a' beads in the 'A' domain aggregate (or cross-linked via hydrogen bonding) into multiple crystalline clusters (\beta-sheet crystals) surrounded by the corona composed of hydrophilic 'b' beads extended towards the aqueous environment. The size of the micelles increases as the 'A'-'B' domain ratio increases and follows the trend: $HA_3B > H(AB)_2 > HAB_3$, due to stronger hydrophobic attractions among the larger amounts of 'a' beads. This computational observation is in good agreement with scanning electron microscopy (SEM) images comparing the three sequences synthesized and purified, as well as the Fourier transform infrared (FTIR) spectroscopy measurements that



Figure 1 | **Integrated fibre design framework and DPD simulation snapshots.** (a) Illustration of the integrated framework that synergistically combines scalable modelling using coarse-graining, genetic silk protein synthesis and shear flow spinning process. Mesoscopic DPD simulation snapshots of the recombinant short silk peptides: (b) HAB₃, (c) H(AB)₂ and (d) HA₃B, with coarse-grained representations (top panel), snapshots after equilibration (middle panel) and after shear flow (bottom panel). Hydrophobic 'a' beads form aggregates (clusters composed of cross-linked β -crystals via hydrogen bonds) and hydrophilic 'b' beads form corona structures around the cluster and physical links between two clusters. The HAB₃ solution exhibits small micellar aggregates (<5 nm in diameter), with a minor increase in micelle size after shear. In contrast, the HA₃B solution exhibits large micellar aggregates (>10 nm in diameter) with enlarged inhomogeneous globular aggregates after shear (15 ~ 20 nm in diameter), which leads to the clogging of the spinning channel. The H(AB)₂ solution exhibits middle-sized homogeneous aggregates (~ 5 nm in diameter), which leads are not shown for clarity and the scale bar applies for all snapshots. Colour code: red beads—hydrophobic 'a' beads in the 'A' domain, blue lines—hydrophilic 'b' beads in the 'B' domain and green lines—hydrophilic 'b' beads in the 'H' domain.

provide the percentages of protein secondary-structure contents (see Supplementary Methods and Supplementary Fig. 3). The observed trend that block copolymers with larger hydrophobic–hydrophilic domain ratios form larger aggregates is in good agreement with other theoretical³¹ and experimental²¹ studies on self-assembly of block copolymers or in general, amphiphilic molecules in aqueous solutions.

Under shear flow, polymer chains extend along the flow stream and the size of micelles increases by merging multiple micelles as the 'a' beads cluster further together (Fig. 1b–d, bottom), in good agreement with earlier theoretical studies on block copolymer micelles, which elongate and aggregate under shear flow³². The aggregate elongation or spherical-to-cylindrical transition under shear flow is not significant for the short sequences studied here, including HAB₃, H(AB)₂ and HA₃B. Such transition is more obvious for longer sequences (discussed later). The change of micelle size in the HAB₃ solution after shearing is modest because each micelle is surrounded by a dense corona of longer hydrophilic chains (Fig. 1b, bottom). In contrast, in the case of the HA₃B solution, the micelles are lumped into globular structures owing to their larger hydrophobic cores and less steric repulsion from the smaller hydrophilic corona (Fig. 1d, bottom). These simulation results are consistent with previous experiments^{33,34} in which pure solutions of the HAB₃ sequence did not form fibres and the HA₃B solution suffered from clogging during the microfluidic processing. Finally, in the case of H(AB)₂, the flow shearing process results in a homogeneous solution of micelles with the size doubled (Fig. 1c, bottom).

Polymer clusters composed of the 'A' domain exhibit physical connections between them when they share the amorphous 'B' domains of the same polymer, which is the key prerequisite for them to assemble into robust silk fibres. To effectively visualize the connectivity between the clusters composed of the particles that define the 'A' domains, we devised a novel node-bridge network diagram (see Methods) in which a 'node' represents the centre of mass of the cluster and a 'bridge' represents the physical link between two nodes. Here, the thickness of each bridge is linearly proportional to the multiplicity of the connections, that is, the number of polymer chains through which two nodes connect. The node-bridge diagrams in Fig. 2a show that only the $H(AB)_2$ sequence enables weak but connected polymer networks both before and after shear flow, compared with the HAB₃ and HA₃B sequences. Time evolution of the network properties (Fig. 2b) show that the median number of 'a' beads per node (as a measure of the aggregate size) is larger for higher 'A'-'B' domain ratios, and that the aggregate size increases significantly after shear flow due to flow-focused concentration. Note that the median value is used instead of the mean value because the cluster size distribution could be highly skewed. In addition, the total number of bridges formed remains zero for high and low 'A'-'B' domain ratios (Fig. 2c), which suggests the advantage of the intermediate domain ratio to allow connected polymer networks and its potential for fibre formation.

The above findings suggest that the delicate balance between the 'A' and 'B' domains are critical for the polymer network connectivity: for large 'A'-'B' domain ratios, there are not enough 'B' domains to form the bridges, whereas for small 'A'-'B' domain ratios, the cluster is too small and fragile to maintain the bridges between them. Therefore, the intermediate 'A'-'B' domain ratio examined here (1:1 for $H(AB)_2$) provides the optimal combination of robust cluster formation and network connectivity. Interestingly, this optimal 1:1 ratio matches the hydrophobic/ hydrophilic domain ratio in the native MaSp1 sequence of *Nephila clavipes*^{19,22}, suggesting an evolutionary principle to adapt certain material properties. For different spider species that already possess close-to-optimal domain ratios, previous literature implies that the major ampullate (dragline) silk mechanical properties could be greatly affected by the small difference in the alanine fractions (one of the major building blocks of the 'A' domain here) of the corresponding silk proteins³⁵. For example, the alanine fraction of *Nephila clavipes* dragline silk is $21.1 \sim 27.5\%$, higher than the alanine fraction of 17.6% for the Araneus diadematus dragline silk, which could lead to the higher Young's modulus of the former silk $(8 \sim 14 \text{ GPa})$ compared with the latter one (~ 4 GPa, ref. 35). Therefore, the polymer domain ratio here also has a strong influence on the structure and mechanics of silk from different spider species. A positive correlation may exist between the alanine fractions in the silk protein and the Young's modulus of silk materials. Other mechanical properties, such as ultimate tensile strength/strain and toughness, will depend on additional factors of the protein sequence, including the amorphous structure of the protein and the resulting protein extensibility.

Effects of sequence length and shear flow. Inspired by the fact that long chain, high molecular weight regenerative silk fibroins have been used as a good additive to fabricate silk fibres³⁴, we then pursued new design improvements using much longer protein sequences based on the model-predicted $H(AB)_2$ sequence with the optimal 'A'-'B' domain ratio. Towards this effort, we carried out a set of new simulations on the $H(AB)_n$



Figure 2 | Polymer network structures for the HAB₃, H(AB)₂ and HA₃B sequences. (a) Polymer network analysis leads to the node-bridge diagram of the three peptide sequences before and after shear flow (all correspond to the simulation snapshots in Fig. 1). Only the H(AB)₂ sequence exhibit weak network connectivity, whereas the other two sequences do not form any network. Time evolution of the simulated polymer network properties during equilibration and shear flow: (b) median number of 'a' beads per node as a measure of the aggregate size and (c) the total number of bridges as a measure of the connectivity. The median size of each aggregate or cluster (b) is increased during the shear flow and the trend is consistent with Fig. 1, while the total number of bridges (c) is reduced for H(AB)₂ during the shear flow and remains zero for both HAB₃ and HA₃B. These results clearly show the advantage of the H(AB)₂ sequence with the intermediate 'A'-'B' domain ratio to form connected polymer networks (highlighted by the red rectangle).

(n = 2, 4, 8 and 12) sequences with increasing multiblock copolymer chain length as the number of repeated units *n* increases (Fig. 3a,b). The molecular weights of different sequences also range from 11,654 to 43,731 Da for n = 2 to 12. In comparison, various MaSp sequences have been shown to contain short peptide motifs that are repeated multiple times with various combinations to form repetitive structural modules, which range in size for the core sequence from n = 19 to 46 (ref. 36). For example, the native MaSp1 sequence possesses short peptide motifs (accession number: P19837.3) with n = 20 (refs 19,22). The messenger RNA sizes for MaSp1 and MaSp2 were shown to be ~12.5 and 10.5 kb, respectively, generating proteins around 350 kDa that contains also the carboxy (C)-/amino (N)-terminals and the spacer groups²². Although the simulations and



Figure 3 | DPD simulation snapshots and polymer network structures for the H(AB)_{*n*} **sequences.** (**a**,**b**) Single protein snapshots for H(AB)_{*4*} and H(AB)₁₂. (**c**,**d**) H(AB)₄ and H(AB)₁₂ results before shear flow (after equilibration). (**e**-**f**) H(AB)₄ and H(AB)₁₂ results after shear flow. Below each simulation snapshot, the corresponding node-bridge diagram is plotted where hydrophobic crystals are represented as red nodes and physical bridges as black lines. The thickness of the black lines is linearly proportional to the multiplicity of the bridge (number of connections). Colour code is the same as in Fig. 1. Note that water beads are not shown for clarity and the scale bar applies for all the snapshots.

experiments here focus on shorter peptides with $n \le 12$ as a proof of concept, they represent the major structural modules of native silk proteins for self-assembly and the findings here should hold their generality. We are also in the progress of expressing and synthesizing longer recombinant silk proteins with *n* values from 20 to 100.

The simulated equilibrium structures of the different $H(AB)_n$ sequences exhibit homogeneously distributed clusters of similar but slightly increased sizes for longer chains (Fig. 3c,d) for comparisons between n = 4 and 12). This finding is consistent with experimental atomic force microscopic (AFM) images of the protein solution (see Supplementary Methods and Supplementary Fig. 4a). However, the network node-bridge diagram of longer chains shows more densely distributed bridges and greatly enhanced the total number of bridges compared with shorter ones (Fig. 3c,d, bottom). Furthermore, for longer chains, we find more multi-connected bridges (thicker black lines in the diagram). The different sequences also show distinct configuration change after the shear flow (Fig. 3e,f for comparison between n = 4 and 12). Aggregate elongation or spherical-to-cylindrical transition under shear flow is very significant for the longer sequences here $(n \ge 4)$, consistent with previous simulation results³². As the polymer chains stretch along the fibre axis (xaxis) under shear flow, the cross-linked β -sheet crystals (composed of the 'A' domains) grow in size until it reaches the steady state for which the overall crystal size increases significantly. This is also consistent with experimental FTIRderived percentages of protein secondary-structure contents for the protein aggregates (see Supplementary Methods and Supplementary Fig. 4b), in which the β -sheet content increases by threefold after fibre spinning. Interestingly, from node-bridge diagrams, we find that the number of multi-connected bridges is greatly enhanced after shear flow, but only longer sequences exhibit homogeneous and continuous networks along the x axis while shorter sequences exhibit only isolated and discontinuous networks (Fig. 3e,f, bottom).

Our simulation well explains, for the first time at the molecular level, the previously observed monotonic increasing trend in fibre mechanics as the recombinant silk protein chain becomes longer, even up to 96 repeated units (molecular weight = 285 kDa) without plateau³⁷. Time evolutions of the polymer network properties (Fig. 4a,b) confirm the observed changes of the median cluster size and total number of bridges of the $H(AB)_n$ sequences during shear flow and subsequent mechanical tensile testing. As discussed earlier, the cluster size shows a weak dependence on the peptide length because it is determined primarily by the composition of the hydrophobic 'A' domains, although shear flow can greatly enlarge the cluster size. The total number of bridges shows a significant dependence on the polymer chain length, however, the total number of bridges is not enhanced at all during shear flow, which is probably due to the flow-induced perturbation and disruption of the network in all directions (isotropic). In analogy to the percolation network, we also computed the distribution of the number of connected nodes for H(AB)₄ and H(AB)₁₂ sequences (Fig. 4d). Two nodes with only single connection between them can be considered as dangling bonds, which do not contribute to the materials strength because they are not stretched under tension. The fraction of such wasted connection is zero for the longer H(AB)₁₂ sequence, suggesting the advantage of longer chain length in spinning robust silk fibres.

To further understand the effect of shear flow on fibre formation, we introduce the measure of network conductance that characterizes the degree of anisotropic polymer alignment and network integrity (percolation) along the x axis (see Methods). Although the total number of bridges is not enhanced during shear flow (Fig. 4b), the network conductance is greatly



Figure 4 | Time evolution of the polymer network properties for the H(AB)_n sequences. (a) Median number of 'a' beads per node as a measure of the aggregate size. (b) The total number of bridges as a measure of the connectivity. (c) The polymer network conductance as a measure of the degree of protein alignment. During both equilibration and shear flow, the median sizes of nodes do not vary a lot among all sequences (a), but longer copolymers have significantly more bridges (b). During shear flow, copolymers are stretched under shear flow and the cross-links are continuously broken and reformed until the steady state is reached for the simulated polymer properties in **a-c**. Although the network connectivity is not increased (in fact, it drops by a little due to shearing-induced perturbation) during shear flow (b), the network conductance for the long sequences (n = 8 and 12) are greatly enhanced due to the shearing-induced polymer alignment (c). The discontinuity between shear flow and tensile stretching periods in **a-c** is due to the stress relaxation simulation (results not reported here) in between the two periods. Interestingly, the shorter sequences (n = 2 and 4) form weak networks that are not able to maintain structural integrity due to the shearing-induced perturbation and, therefore, their network conductance drops to zero (c). (d) The distribution histograms of the numbers of connected nodes for H(AB)₄ and H(AB)₁₂ after shear flow. The H(AB)₁₂ sequence has node connectivity distribution peaks at higher values (\sim 5) than H(AB)₄ (\sim 2).

increased during shear flow (Fig. 4c). This reveals the most important influence of shear flow in helping align the originally isotropic polymer chains and assemble them into anisotropic structures with good network connections. Interestingly, only the conductance of longer protein sequences (n=8 and 12) are enhanced during shear flow, while the shorter ones drop to zero due to flow-induced disruption only along the x axis. This orientational effect, as a result of the shear flow, determines the critical polymer length $(n \ge 8)$ beyond which silk formation becomes possible. A theoretical model based on the network percolation theory is used to explain such critical polymer length, as well as the optimal 'A'-'B' domain ratio observed above (see Supplementary Discussion). More importantly, shearing-induced polymer alignments need to overcome flow-induced network perturbations to sustain structural integrity along the x axis. Therefore, longer protein sequences are better candidates due to their pre-existing multiply connected network even before shear flow.

Anisotropic polymer network conductance and fibre mechanics. To understand the effect of polymer network microstructures on mechanical properties of the silk fibres, we performed tensile loading simulations on the network structures formed before and after shear flow (Fig. 5a,b). As expected from the enhanced number of bridges and conductance for longer sequences, the Young's modulus is superior for longer protein chains both before and after shear flow. Specifically, the longest $H(AB)_{12}$ sequence leads to fibre formation after shear flow and exhibit the highest Young's modulus of 3.5 MPa. Polymer networks formed before shear flow (Fig. 5a) are weak with softening behaviours at high tensile strains, while the ones formed after shear flow (Fig. 5b) exhibit stiffening behaviours. Interestingly, we found that after shear flow (Fig. 5b) the Young's modulus of the network increases by about two times for longer sequences (n = 8 and 12), but drops to zero for shorter sequences (n = 2 and 4). The network microstructure evolution during tensile tests is shown in Fig. 5c for $H(AB)_{12}$ sequences, which exhibits three deformation steps: extension of individual polymer chains and bridges (soft hydrophilic 'B' domains forming amorphous phases) between clusters (stiff hydrophobic 'A' domains forming cross-linked βsheet crystals), the escape and breakage of polymer chains from the cluster and sequential unfolding of polymer chains in the cluster. Our simulation results confirm the proposed deformation mechanism from the experimental tensile loading test of silk fibre accompanied by X-ray scattering38.

In support of our modelling results, we carried out a series of experimental studies that focused on the $H(AB)_{12}$ sequences (see Supplementary Methods and Supplementary Fig. 5). SEM images of $H(AB)_{12}$ in aqueous solutions show fibre-like structures and nano-fibre (within the film) features for self-assembled $H(AB)_{12}$ polymers (Supplementary Fig. 5a), suggesting a high possibility of them forming silk fibres in a shear flow device. The original dried $H(AB)_{12}$ film Young's modulus was characterized using AFM nanoindentation. The resulting Young's modulus map and



Figure 5 | Tensile mechanical tests of the H(AB)^{*n*} **sequences using the mesoscale model.** (**a**,**b**) Stress-strain curves for mechanical tensile tests of polymer networks before and after shear flow. Before the shear flow, all networks are weak without stiffening at high tensile strains (low maximum stress), and it follows the trend that longer sequences are stronger with higher Young's modulus. After the shear flow, the network Young's modulus remains the same except that the Young's modulus for the two shorter sequences (n = 2 and 4) drops to zero, and the longer sequences are stronger with much higher maximum stress and stiffening behaviour at high tensile strains. Note that due to the coarse-grained nature of the DPD model, the absolute stress values are approximate and we will focus on the relative values and comparisons among different protein sequences in a qualitative way. This factor, in addition to the presence of solvents in simulations, would also lead to simulated ultimate network strains much higher than that of common silk fibres ($10\% \sim 30\%$, ref. 36.) Therefore, simulation predicted quantitative Young's modulus values are not to be compared with the later experimental tensile testing results. (**c**) Schematic of the H(AB)₁₂ network deformation process under various tensile strains. The red clusters (stiff cross-linked β -sheet crystals) slightly deform during stretching and maintain their structural integrity, while the blue bridges (soft amorphous regions) deform significantly or even break to release the applied stress.

distribution show that the original $H(AB)_{12}$ films possess a Young's modulus of only 20~40 MPa (Supplementary Fig. 5b). Successful spinning of macroscopic fibres (~1 cm long) using the $H(AB)_{12}$ sequence dissolved in two different solvents (aqueous LiBr solution and hexafluoroisopropanol (HFIP) with formic acid) is confirmed by both bright-field optical microscope and SEM images (Fig. 6). The resulting concentrated silk solution was dialysed extensively against water to remove unnecessary LiBr ions (with a dilution factor of 1 to 2,000), which could be close to the natural spider silk-spinning condition (ionic environment with Na⁺ and K⁺, ref. 30) and is consistent with the DPD modelling framework. The syringe needle fibre-spinning method is used here. As shown in Fig. 6a, $H(AB)_{12}$ polymers dissolved in HFIP can be spun into fibres that form bundles in the 2-propanol coagulation bath, consistent with our model predictions for longer chain polymers. The bundle delaminates and super-contracts after rehydrating by water, which results in individually separated fibres with relatively uniform diameters ($D \sim 8 \,\mu$ m) under SEM (Fig. 6b). The hierarchical structure of the fibre bundle after 2-propanol treatment (dried without hydration) was probed in a series of SEM images (Supplementary Fig. 6), showing the spherical H(AB)₁₂ protein aggregates as the fundamental building block of the fibre bundle, similar to our model-predicted morphology in Fig. 3d. In addition, H(AB)₁₂ polymers dissolved in aqueous LiBr solution form thinner individual fibres ($D \sim 3 \,\mu$ m for dried fibres) without bundling



Figure 6 | Experimental validations for fibre spinning and mechanical properties. Syringe needle spinning of recombinant silk fibres with the $H(AB)_{12}$ polymer dissolved in HFIP: (a) bright-field microscopic images of spun fibres in bundle in the coagulation bath and (b) SEM images of the separated fibre after rehydration, showing a relatively uniform fibre diameter of ~8 μ m. In addition, $H(AB)_{12}$ polymer dissolved in LiBr aqueous solution can also form thinner silk fibres without bundling: (c) bright-field microscopic images in the coagulation bath and (d) SEM images of the dried fibre showing a diameter of ~3 μ m. Mechanical properties of syringe needle spun silk fibres using the $H(AB)_{12}$ sequence dissolved in two different solvents (HFIP and LiBr aqueous solution). The effect of hydration on fibre Young's modulus is studied by comparing air dried and rehydrated fibres. (e) The Young's modulus maps (top) and the corresponding Young's modulus distributions (bottom) of the four different types of fibres were obtained using the similar nanoindentation measurement as in Supplementary Fig. 5b. The red colour in the Young's modulus map indicates outliers with extremely high Young's modulus values. (f) Averaged fibre Young's modulus values over the distribution plots in e, showing standard deviations. (g) Representative stress-strain curve from mechanical tensile testing on various silk fibre samples, confirming high fibre robustness and Young's modulus.

(Fig. 6c,d). On the other hand, shorter sequences such as $H(AB)_2$ only form disordered films when dissolved in both solvents (Supplementary Fig. 7), which is in good agreement with our model predictions about the effect of polymer chain length on fibre formation.

The mechanical properties of four different types of spun fibres (with two solvent, and for air dried or rehydrated cases) were characterized using AFM nanoindentation (Fig. 6e). The rehydrated fibres will fill the purpose of testing the effect of hydration on fibre mechanics. Overall, the spun $H(AB)_{12}$ fibres exhibit a greatly enhanced Young's modulus modulus of $1 \sim 8$ GPa (Fig. 6f), with two orders of magnitude enhancement over the original dried films (Supplementary Fig. 5 (b)). More excitingly, the spun fibres here are very close to natural spider silk fibres with an initial Young's modulus of $3 \sim 20$ GPa, depending on spider species^{36,39}. Mechanical tensile testing along the fibre axis also confirms their robustness with a tensile strength of \sim 23 MPa, a Young's modulus of \sim 500 MPa and an ultimate strain of 6% (Fig. 6g). The fibre tensile testing results are not comparable with the nanoindentation results due to the fact that the tensile loading was introduced on fibre bundles ($>100 \,\mu m$ in diameter) instead of individual fibres ($< 10 \,\mu\text{m}$ in diameter), for which individual fibre sliding along the pulling direction would diminish the ultimate fibre mechanical performance. These experimental findings agree very well with the modelpredicted enhancement in the polymer network Young's modulus modulus after shear flow treatment (Fig. 5), confirming that flowfocusing and shearing in the spinning process can indeed facilitate the assembly of silk fibres by aligning individual polymer chains.

Discussion

On the basis of the simulation results for the $H(AB)_n$ sequences, we summarize the correlation between various steady-state polymer network and mechanical properties with the number of repeated polymer units n in Fig. 7a. In general, all polymer networks and mechanical properties (aggregate size, network connectivity, network conductance and Young's modulus) correlate well with the value of *n*, except that the network conductance and both mechanical properties remains zero for shorter chain lengths (n=2 and 4) after shear flow due to destruction of the network along only the fibre axis. More importantly, we summarize the correlation between total number of bridges and conductance with the resulting Young's modulus in Fig. 7b. The total number of bridges correlates well with the Young's modulus before shear flow, as predicted by classical polymer theory, but cannot explain the zero Young's modulus for shorter chains (n = 2 and 4) after shear flow (Fig. 7b, top). This is because the total number of bridges does not represent the heterogeneity of the network connectivity and thus cannot capture the percolation of network. On the other hand, the network conductance not only explains the zero Young's modulus for shorter chains (n = 2 and 4) after shear flow, but also exhibits perfect linear correlation with the Young's modulus for all polymer chain lengths both before and after shear flow (Fig. 7b, bottom) because it measures the contribution from the bridges to the anisotropic silk Young's modulus along the fibre axis. We can demonstrate the perfect correlation between the network conductance and the Young's modulus by making an analogy between elastic spring network and resistance network (see Supplementary Discussion and Supplementary Fig. 8), extending



Figure 7 | **Summary of modelling results and fibre design trends.** (a) The effect of polymer chain length (measured by the number of repeated polymeric units, *n*) of the $H(AB)_n$ sequences on simulated steady-state polymer network properties, and the corresponding Young's modulus before and after shear flow. All three polymer network properties correlate well with the value of *n*, except that the network conductance remains zero for shorter chain length (n = 2 and 4) after shear flow due to shearing-induced perturbations. The Young's modulus also correlates well with the value of *n*, except that, for n = 2 and 4, the mechanical values remain zero after shear flow, as a result of discontinuous networks with zero conductance. (b) Correlations between total number of bridges and conductance of the $H(AB)_n$ sequences with simulated Young's modulus. The total number of bridges correlates with the Young's modulus before shear flow, but cannot explain the zero values for shorter chains (n = 2 and 4) after shear flow. On the other hand, the network conductance correlates perfectly well with the Young's modulus both before and after shear flow, representing an extension of the classical polymer theory to heterogeneous fibres (see Supplementary Fig. 8).

the prediction of the classical polymer theory to heterogeneous fibres (recovering the limiting homogeneous case). As a result, we find that the network conductance instead of the total number of bridges is a good measure of network connectivity and thus is a key parameter for the predictive design of biological silk fibres, as demonstrated in Fig. 7b.

In conclusion, we provide a generic design principle for general multiblock copolymers $(A_pB_q)_n$: (i) intermediate p:q ratio leads to balanced hydrophobicity, which is desirable to process homogeneous gels with well-connected polymer networks both before and during spinning, and (ii) large n value not only enhances network connectivity before spinning but is also necessary to retain network percolation against shear-induced disruption. Although longer protein sequences are preferred, the solubility of copolymers decreases as the length increases due to entropy reduction, which sets a limit on n to maintain solubility. Also, longer copolymer chains have slower dynamics, which could not be processed appropriately during the allowed processing time for shear flow spinning. To extend the simulation to much longer polymers approaching that of native silk proteins, a more timeefficient computational approach is in progress, for example, by modelling solvent molecules implicitly. We reveal that the anisotropic conductance of polymer networks (the alignment of bridges and percolation property) is more critical than the crosslinked β-sheet crystals and the total number of bridges for the ultimate mechanical properties of the silk fibre. Thus, we establish that network conductance is a proper measure of network connectivity and Young's modulus. Overall, this work systematically studies the sequence-structure-process-property relationships for producing artificial silk fibres using synthetic silk protein sequences and optimized shear-flow fibre-assembly protocol. In this work, we extended classical polymer theory, which describes only homogeneous polymer aggregates, with insights from a percolation network model that also is capable of describing heterogeneous polymer networks after spinning. The scalable models presented here, validated by experiments, can enable predictive designs of hierarchical materials with not only outstanding mechanical, but also promising transport properties (optical, electrical, thermal and others) by constructing network topologies and models that capture material structures and features at the molecular level.

Methods

DPD simulation setup. All DPD simulations are carried out using the massively parallelized LAMMPS package⁴⁰. The simulations run in an elongated rectangular box (60 × 40 × 40 R_c^3 , where $R_c = 9.321$ Å is the characteristic/physical length scale in the DPD model here) with a square cross-section and periodic boundary condition. The box length in the x axis (direction of flow) was chosen to be longer than a single extended chain, to avoid artifacts from boundary conditions. The concentration is fixed to 20% volume fraction of coarse-grained polymer beads (each representing three amino acids) in all the cases to match the experimental spinning condition. The total number of beads in a system is 288,000 for studying the HAB₃, H(AB)₂ and HA₃B systems. Note that when comparing among the $H(AB)_n$ (n = 2, 4, 8 and 12) systems, the simulation box size is increased to $120 \times 80 \times 40 R_c^3$ with a total number of 1,152,000 beads due to the longer polymer chains involved. For the starting structure, we grow peptides chains randomly with a fixed distance a (where a is the equilibrium bond distance in the chain) between beads in the simulation box, up to 20% of the volume fraction. We then fill the box with solvent beads until the number density of 3 is reached. After creating the initial random structure, we simulate the spinning process via several steps. All DPD simulations run under the NVE ensemble with a fixed time step of $\Delta t = 0.03 \tau$, where $\tau = 0.75$ ns is the characteristic/ physical time scale in the DPD model here. First, equilibration simulation is performed until a steady state is achieved, by tracking root-mean-square-deviation for 210,000 time steps. Second, a shear rate of $\dot{\gamma}_{xy} = 0.01 \tau^{-1}$ is applied along the *x* axis (normal to the *y* axis) for 420,000 time steps to mimic the fibre-spinning process. The Lees-Edwards boundary conditions were applied to generate the shear flow⁴¹ such that the same shear rate above was applied to all the materials in the system. Details on the DPD formalism and the parameterization procedure can be found in the Supplementary Methods. Equilibrations of self-assembled aggregates without and with shear flow were confirmed by the plateau in the time evolutions of the size of aggregates (or number of beads per node) and the number of bridges

before shear (the equilibration period) and during the shear flow (Figs 2 and 4), respectively. Another 100,000 time steps without shear were used to equilibrate the system after the shear flow, followed by the tensile simulations below. The aggregates that are enlarged due to shear flow will not break up after cessation of shear, although minor breakups were observed for aggregates composed of polymers of shorter chain length (data not shown). This implies that the simulated system after shear (with larger aggregates and better network connectivity) is kinetically (not thermodynamically) stable, compared with the thermodynamically stable system (with smaller aggregates and fewer network connections) before shear. The energy barrier for the transition from the sheared state to a lower energy state would be higher for longer polymers, possibility due to the entanglement (gelation) of longer chains, which prevents immediate aggregate breakups during the relatively short equilibration run.

Polymer network analysis. We define that two 'a' beads in the 'A' domain are connected if they are located within 0.94 Re which is the averaged value of the first neighbour-neighbour distance 0.78 Rc and the second neighbour-neighbour distance 1.10 Rc. A cluster, that is, the aggregated β-sheet crystals (cross-linked via hydrogen bonds), is defined as the group of connected 'a' beads. The depth-first search algorithm is used to find the cluster distribution efficiently. Once cluster distribution is obtained, each isolated cluster is defined as a 'node' whose coordinate is defined as the centre of mass of 'a' beads in the cluster. Two nodes are defined to be connected with one 'bridge' if they are linked via the 'B' domain of at least one polymer chain. The number of connections between two nodes is defined as the multiplicity of the bridges, that is, the number of polymers through which they are linked. On the basis of the node connectivity, adjacency matrix is constructed that is used to generate the node-bridge diagrams. The conductance of the polymer network along the x axis is computed by drawing conceptual parallels with the resistance model of a typical electrical network⁴², in which one bridge possesses a conductance of 1 (that is, the no bridge case possesses zero conductance) and a voltage of 1 is applied between the left and the right boundaries. A similar study was reported recently on the structural network evolution of colloidal gels under shear flow using Brownian dynamics simulations⁴³.

Mechanical property modelling. The mechanical property of the copolymer network before and after applying the shear flow is investigated using the standard tensile simulations along the x axis. The entire simulation box containing copolymers and the solvents is stretched in the x axis at a constant engineering strain rate of $7.5 \times 10^{-6} \tau^{-1}$, while the y and the z dimensions are adjusted simultaneously (with their aspect ratio fixed) to maintain the constant volume of the simulation box. The Young's modulus (Young's modulus) of the network in the x axis, E_{xx} can be obtained from the three-dimensional system using the equation: $E_x = \frac{\sigma_x - v(\sigma_y + \sigma_z)}{\sigma_x}$, where σ_i (i = x, and z) is the normal stress tensor value along the *i* axis, \hat{e}_x is the strain along the *x* axis, and the Poisson's ratio v = 0.5 for the constant volume constraint we enforced (incompressible). The effective stress can be then defined as $\sigma_{eff} = \sigma_x - v (\sigma_y + \sigma_z)$ and the linear-elastic region (for $\varepsilon_x \le 50\%$) of the stress-strain curve is used for determining E_x . To remove the effect of solvents on E_x , we corrected the value of E_x by dividing it with the ratio between the volume of the entire simulation box and the effective volume occupied by the assembled copolymers. The DPD units for stress/pressure is $k_B T/R_c^3 = 1$, which can be converted to the physical units of 5.11 MPa at 300 K. Note that the simulated system right after shear flow is already pre-stretched with $\sigma_{eff} > 0$ and therefore, a compressive simulation (using the same method as the tensile simulation, but with a negative strain rate of $-5 \times 10^{-6} \tau^{-1}$) is carried out first to relax the system and determine the stress-free configuration at which $\sigma_{eff}=0$. The stress-free system, with a reduced box dimension along the *x* axis (~70% of the original value), is then used as the new reference for the subsequent tensile simulation.

Silk block copolymer biosynthesis and characterizations. Synthetic or recombinant multiblock copolymer-like silk peptides and proteins (HAB₃, HA₃B and H(AB)_n (n = 2, 4, 8 and 12) sequences) were cloned, expressed and purified according to the previously established procedure by Rabotyagova *et al.*^{44,45} The purity of expressed proteins was verified by SDA-polyacrylamide gel electrophoresis (SDS-PAGE) electrophoresis followed by Colloidal Blue staining. Protein identity was confirmed by matrix-assisted laser desorption ionization mass spectrometry (Tufts Core Chemistry Facility, Boston, MA).

SEM was used to assess morphological characterization of all spider silk block copolymers. The experiments were performed using a Zeiss 55Ultra System (Harvard University Center for Nanoscale Systems, Cambridge, MA). Each sample was sputter-coated with platinum with a HAR024 sputter coater and mounted onto a sample holder with conductive tape. Lyophilized peptides were dissolved in water to a final concentration of 1 mg ml⁻¹ and dried on a silicon chip in a closed container at room temperature. Images were taken using InLense and SE2 detectors at 1 keV.

Sample dried films ~ $10 \,\mu\text{m}$ in thickness were cast onto CaF₂ substrate for the FTIR spectroscopy measurements. FTIR was carried out on a Jasco FT/IR-6200 spectrometer with a TGS detector. The absorbance spectra were obtained by averaging 128 scans with a resolution of $4.0 \,\text{cm}^{-1}$. The background spectra were collected under the same conditions and subtracted from the scan for each sample. We then carried out Fourier self-deconvolution over the amide I peaks on the

resulting FTIR spectra, using Opus 5.0 software with Lorentzian peak profile (halfbandwidth of 25 cm^{-1} and a noise reduction factor of 0.3). This renders individual spectrum, which was used to obtain the composition (in percentage) of different protein secondary-structure contents by integrating the area of each deconvoluted curve, and then normalizing to the total area of the amide I peak. FTIR spectra and the corresponding Fourier self-deconvolution data for the H(AB)₂ sequence and the H(AB)₁₂ sequence before and after spun are shown in Supplementary Fig. 9.

AFM imaging and force spectroscopy measurements were performed on an Asylum Research MFP-3D-Bio AFM (Asylum Research, an Oxford Instruments Company, Santa Barbara, CA). For imaging in fluids, 80 µl sample of 1% w/v was deposited as a drop on a silicon substrate and imaged. IgorPro 6.22A image analysis software was used to determine the heights of observed structures. The root-mean-square and the arithmetic average height (*R*a) were determined using software to find differences between roughnesses of samples. Force curves were obtained with AFM in the contact mode. All imaging was performed in contact mode using Olympus silicon probes on a silicon surface. Cantilever specifications are the following: 160 µm in length, 40 µm in width, with a resonant frequency of 300 ± 50 kHz.

Syringe spinning of silk fibres and characterization. Syringe fibre spinning was carried out following the protocol in previous work⁴⁶ using 15% w/v recombinant silk protein solutions, H(AB)2 and H(AB)12, synthesized in this work. The experimental setup is shown in Supplementary Fig. 10, with two different solvents (95% HFIP with 5% formic acid, or 9M LiBr aqueous solution after 1-h dialysis against water) being used for dissolving the proteins to fine-tune their aggregation. The extensive dialysis (100 ml solution against 21 water) removes unnecessary ions. In brief, the protein solutions are extruded at a speed of 15 µl min⁻¹ through a stainless-steel syringe needle (22 G, 127 micron, Hamilton) into 90% 2-propanol coagulation bath to form fibres. The spinning mimics aspects of native silk processing in a tunable manner via hydrodynamic flow focusing and shearing. After the fibres were formed (only with H(AB)₁₂) and air dried, we rehydrated some of them by immersing them into water to study the hydration effect on fibre mechanical properties. SEM images were taken on each fibre sample with the same parameters mentioned earlier except that the operating voltage was enhanced to 5 keV with an InLense detector.

AFM nanoindentations of the original dried H(AB)12 films and the spun H(AB)₁₂ fibres were carried out using the same AFM device mentioned earlier. Local Young's modulus (Young's modulus) of the film was calculated using the force versus indentation depth curve (Supplementary Fig. 11) and based on detailed procedures and equations in the work by Spedden and Staii⁴⁷. The Young's modulus map and distribution were obtained by scanning a squared region $(20 \times 20 \,\mu s^2)$ on each sample and collecting various local Young's modulus values on a much smaller subregion $(2 \times 2 \mu s^2)$. The indentations on four different types of H(AB)₁₂ fibres (dissolved in two solvents, dried or rehydrated) were carried out using an AC160TS-R3 cantilever (spring constant 26 N m $^{-1})$ on a $10 \times 10 \, \mu s^2$ squared region. Tensile measurements of spun fibres were performed on an Instron microtester (Instron, Norwood, MA) with a 5 N load cell. Samples were stuck to a custom frame to prevent them from breaking prematurely. Once the samples were loaded, the frames were removed and the fibres were pulled at 0.01 s $^{-1}$ strain rate until failure. Force data were collected and normalized to stress values on the basis of respective diameter measurements. Fibre diameters were determined using light microscopy under $\times 20$ magnification.

References

- Jin, H. J. & Kaplan, D. L. Mechanism of silk processing in insects and spiders. Nature 424, 1057–1061 (2003).
- Schafer, A., Vehoff, T., Glisovic, A. & Salditt, T. Spider silk softening by water uptake: an AFM study. *Eur. Biophys. J.* 37, 197–204 (2008).
- Grujicic, M. *et al.* Multi-length scale computational derivation of Kevlar[®] yarnlevel material model. *J. Mater. Sci.* 46, 4787–4802 (2011).
- Vollrath, F. & Knight, D. P. Liquid crystalline spinning of spider silk. *Nature* 410, 541–548 (2001).
- 5. Altrman, G. H. et al. Silk-based biomaterials. Biomaterials 24, 401-416 (2003).
- 6. Jelinski, L. W. Establishing the relationship between structure and mechanical function in silks. *Curr. Opin. Solid State Mater. Sci.* **3**, 237–245 (1998).
- 7. Altman, G. H. et al. Silk-based biomaterials. Biomaterials 24, 401-416 (2003).
- Allmeling, C., Jokuszies, A., Reimers, K., Kall, S. & Vogt, P. M. Use of spider silk fibers as an innovative material in a biocompatible artificial nerve conduit. *J. Cell. Mol. Med.* **10**, 770–777 (2006).
- Chao, P. H. G. et al. Silk hydrogel for cartilage tissue engineering. J. Biomed. Mater. Res. B Appl. Biomater. 95B, 84–90 (2010).
- MacIntosh, A. C., Kearns, V. R., Crawford, A. & Hatton, P. V. Skeletal tissue engineering using silk biomaterials. *J. Tissue Eng. Regen. Med.* 2, 71–80 (2008).
- Numata, K., Hamasaki, J., Subramanian, B. & Kaplan, D. L. Gene delivery mediated by recombinant silk proteins containing cationic and cell binding motifs. *J. Control. Release* 146, 136–143 (2010).

- Lammel, A., Schwab, M., Hofer, M., Winter, G. & Scheibel, T. Recombinant spider silk particles as drug delivery vehicles. *Biomaterials* 32, 2233–2240 (2011)
- Holland, C., Terry, A. E., Porter, D. & Vollrath, F. Natural and unnatural silks. *Polymer* 48, 3388–3392 (2007).
- Jin, H. J., Fridrikh, S. V., Rutledge, G. C. & Kaplan, D. L. Electrospinning Bombyx mori silk with poly(ethylene oxide). Biomacromolecules 3, 1233–1239 (2002).
- Wang, M., Jin, H. J., Kaplan, D. L. & Rutledge, G. C. Mechanical properties of electrospun silk fibers. *Macromolecules* 37, 6856–6864 (2004).
- Guerette, P. A., Ginzinger, D. G., Weber, B. H. & Gosline, J. M. Silk properties determined by gland-specific expression of a spider fibroin gene family. *Science* 272, 112–115 (1996).
- 17. Lazaris, A. *et al.* Spider silk fibers spun from soluble recombinant silk produced in mammalian cells. *Science* **295**, 472–476 (2002).
- Rammensee, S., Slotta, U., Scheibel, T. & Bausch, A. R. Assembly mechanism of recombinant spider silk proteins. *Proc. Natl Acad. Sci. USA* 105, 6590–6595 (2008).
- Lewis, R. V. Spider silk: ancient ideas for new biomaterials. Chem. Rev. 106, 3762–3774 (2006).
- Xu, M. & Lewis, R. V. Structure of a protein superfiber—spider dragline silk. Proc. Natl Acad. Sci. USA 87, 7120-7124 (1990).
- Mai, Y. Y. & Eisenberg, A. Self-assembly of block copolymers. *Chem. Soc. Rev.* 41, 5969–5985 (2012).
- Padmanabhan, P., Chavis, M., Ober, C. K. & Escobedo, F. A. Phase behaviour of PMMA-b-PHEMA with solvents methanol and THF: modelling and comparison to the experiment. *Soft Matter* 10, 6172–6181 (2014).
- Matsen, M. W. & Schick, M. Stable and unstable phases of a diblock copolymer melt. *Phys. Rev. Lett.* 72, 2660–2663 (1994).
- Keten, S., Xu, Z. P., Ihle, B. & Buehler, M. J. Nanoconfinement controls Young's modulus, strength and mechanical toughness of beta-sheet crystals in silk. *Nat. Mater.* 9, 359–367 (2010).
- Keten, S. & Buehler, M. J. Nanostructure and molecular mechanics of spider dragline silk protein assemblies. J. R. Soc. Interface 7, 1709–1721 (2010).
- 26. Keten, S. & Buehler, M. J. Atomistic model of the spider silk nanostructure. *Appl. Phys. Lett.* **96**, 153701 (2010).
- Groot, R. D. & Warren, P. B. Dissipative particle dynamics: bridging the gap between atomistic and mesoscopic simulation. *J. Chem. Phys.* 107, 4423–4435 (1997).
- Chen, S., Phan-Thien, N., Fan, X. J. & Khoo, B. C. Dissipative particle dynamics simulation of polymer drops in a periodic shear flow. *J. NonNewton. Fluid. Mech.* 118, 65–81 (2004).
- Eisoldt, L., Hardy, J. G., Heim, M. & Scheibel, T. R. The role of salt and shear on the storage and assembly of spider silk proteins. *J. Struct. Biol.* 170, 413–419 (2010).
- Chen, X., Shao, Z. Z. & Vollrath, F. The spinning processes for spider silk. Soft Matter 2, 448–451 (2006).
- Sheng, Y. J., Wang, T. Y., Chen, W. M. & Tsao, H. K. A-B diblock copolymer micelles: effects of soluble-block length and component compatibility. J. Phys. Chem. B 111, 10938–10945 (2007).
- Chremos, A., Chaikin, P. M., Register, R. A. & Panagiotopoulos, A. Z. Sphereto-cylinder transitions in thin films of diblock copolymers under shear: the role of wetting layers. *Macromolecules* 45, 4406–4415 (2012).
- Kinahan, M. E. et al. Tunable silk: using microfluidics to fabricate silk fibers with controllable properties. Biomacromolecules 12, 1504–1511 (2011).
- Krishnaji, S. T. *et al.* Sequence-structure-property relationships of recombinant spider silk proteins: integration of biopolymer design, processing, and modeling. *Adv. Funct. Mater.* 23, 241–253 (2012).
- Blackledge, T. A., Kuntner, M., Marhabaie, M., Leeper, T. C. & Agnarsson, I. Biomaterial evolution parallels behavioral innovation in the origin of orb-like spider webs. *Sci. Rep.* 2 (2012).
- Agnarsson, I., Kuntner, M. & Blackledge, T. A. Bioprospecting finds the toughest biological material: extraordinary silk from a giant riverine Orb spider. *PLoS ONE* 5, e11234 (2010).
- Xia, X. et al. Native-sized recombinant spider silk protein produced in metabolically engineered *Escherichia coli* results in a strong fiber. Proc. Natl Acad. Sci. USA 107, 14059–14063 (2010).
- Du, N., Yang, Z., Liu, X. Y., Li, Y. & Xu, H. Y. Structural origin of the strainhardening of spider silk. Adv. Funct. Mater. 21, 772–778 (2010).
- Elices, M. et al. Mechanical behavior of silk during the evolution of Orb-web spinning spiders. Biomacromolecules 10, 1904–1910 (2009).
- 40. Plimpton, S. Fast parallel algorithms for short-range molecular dynamics. *J. Comput. Phys.* **117**, 1–19 (1995).
- Lees, A. W. & Edwards, S. F. The computer study of transport processes under extreme conditions. J. Phys. C 5, 1921 (1972).
- Hu, N., Karube, Y., Yan, C., Masuda, Z. & Fukunaga, H. Tunneling effect in a polymer/carbon nanotube nanocomposite strain sensor. *Acta. Mater* 56, 2929–2936 (2008).

ARTICLE

- Park, J. D. & Ahn, K. H. Structural evolution of colloidal gels at intermediate volume fraction under start-up of shear flow. *Soft. Matter* 9, 11650–11662 (2013).
- Rabotyagova, O. S., Cebe, P. & Kaplan, D. L. Self-assembly of genetically engineered spider silk block copolymers. *Biomacromolecules* 10, 229–236 (2009).
- Rabotyagova, O. S., Cebe, P. & Kaplan, D. L. Role of polyalanine domains in beta-sheet formation in spider silk block copolymers. *Macromol. Biosci.* 10, 49–59 (2010).
- Teule, F. et al. A protocol for the production of recombinant spider silk-like proteins for artificial fiber spinning. Nat. Protoc. 4, 341–355 (2009).
- Spedden, E. & Staii, C. Neuron biomechanics probed by atomic force microscopy. Int. J. Mol. Sci. 14, 16124–16140 (2013).

Acknowledgements

We acknowledge support from NIH (U01 EB014967) with additional support from NSF and ONR-PECASE. SEM experiments were performed in part at the Center for Nanoscale Systems (CNS), a member of the National Nanotechnology Infrastructure Network (NNIN), which is supported by the National Science Foundation (NSF) under NSF award No. ECS-0335765. CNS is part of Harvard University. S.L. is additionally supported by the startup funding from the Energy & Materials Initiative at the Florida State University. S.R. is supported by Basic Science Research Program through the National Research Foundation of Korea (NRF) funded by the Ministry of Science, ICT & Future Planning (2013R1A1A010091). N.M.P. is supported by the European Research Council (ERC StG Ideas 2011 BIHSNAM no. 279985 on 'Bio-Inspired hierarchical supernanomaterials', ERC PoC 2013-1 REPLICA2 no. 619448 on 'Large-area replication of biological anti-adhesive nanosurfaces', ERC PoC 2013-2 KNOTOUGH no. 632277 on 'Super-tough knotted fibers'), by the European Commission under the Graphene Flagship (WP10 'Nanocomposites', no. 604391) and by the Provincia Autonoma di Trento ('Graphene Nanocomposites', no. S116/2012-242637 and reg. delib. no. 2266). We also acknowledge Nick Hall and Nicholas Rim at Boston University and Elise Spedden at Tufts University for help with the spinning process, fibre tensile testing and AFM nanoindentation study.

Author contributions

M.J.B., D.L.K. and J.Y.W. designed the research. S.L., S.R. and G.G. implemented the DPD model and analysis tools, carried out the simulations, collected the data and organized the manuscript. O.T. synthesized silk polymers, spun fibres (with M.M.J.) and collected the SEM data. W.H. collected the FTIR data. O.T., D.R. and C.S. collected the AFM and nanoindentation data. M.M.J. and D.L. performed the fibre tensile tests. N.M.P. and S.R. implemented and applied the network percolation model. All the authors contributed to the manuscript writing.

Additional information

Supplementary Information accompanies this paper at http://www.nature.com/ naturecommunications

Competing financial interests: The authors declare no competing financial interests.

Reprints and permission information is available online at http://npg.nature.com/ reprintsandpermissions/

How to cite this article: Lin, S. *et al.* Predictive modelling-based design and experiments for synthesis and spinning of bioinspired silk fibres. *Nat. Commun.* 6:6892 doi: 10.1038/ncomms7892 (2015).



Supplementary Figure 1 | (a) Force extension curves of 27 amino-acid-long worm like chain (WLC) and extensible WLC (EWLC) in comparison of our extensible freely jointed chain (EFJC). Here, WLC are plotted with experimentally obtained persistence length and EWLC is plotted with the chain stiffness obtained from atomistic simulation. Despite of simplicity, our model capture the overall force extension curve of the single peptide chain. (b) Hybrid DPD and HB potential for "a" bead attractive interaction. The short range modified harmonic potential and DPD potential are overlaid to have the minimum energy of $-2.85 k_BT$ at $r = 0.778 R_c$.



Supplementary Figure 2 | (a) Velocity and (b) temperature profile along y direction, after shear flow simulation with $\dot{\gamma}_{xy} = 0.01$ and $L_y = 40$. The velocity profile is obtained by averaging v_x of particles within 40 different sections with height 1, after steady state has been reached. Temperature values for each section are obtained by averaging temperature computed from thermal velocity, i.e., absolute velocity subtracted by translational velocity of each section. Except the boundary region, translational velocity profile changes linearly, achieving Couette flow condition. The temperature profile shows slight deviation from the expected value of 1.0, but the deviation is within 4%, and its effect on the assembly process is negligible.



Supplementary Figure 3 | Experimental SEM images of (a) HAB₃, (b) H(AB)₂, and (c) HA₃B peptide sequences in aqueous solutions after synthesis and purification. The HAB₃ sequence forms perforated films with a pore size of ~ 200 nm. Small spherical aggregates are also observed for the HAB₃ sequence (the zoom-in plot at the bottom) with diameters ranging between 50 and 200 nm. In contrary, the HA₃B sequence forms large microspheres with diameters ranging between 0.5 and 5 μ m. The zoom-in plot at the bottom shows a few small microspheres with diameters of ~ 1 μ m. The H(AB)₂ sequence forms condensed films composed of intermediate-sized spherical aggregates with diameters ranging between 0.2 and 0.6 μ m. (d) Experimental FTIR-derived percentages of the protein secondary-structure contents for the three peptides sequences. The size of the peptide aggregate (center around the β -sheet crystals) correlates directly with the ordered (β -sheet and helical) content and is consistent with the trend observed from the SEM images, i.e., peptides with larger "A"-"B" domain ratios forms larger aggregate structures. (e) DPD simulated median number of "a" beads per node (or aggregate size) after equilibration as a quantitative measure of the ordered contents, which correlates perfectly well with the SEM and FTIR results. The lower and upper error bars are the 25% and 75% percentiles of all aggregate sizes, respectively.



Supplementary Figure 4 | Experimental AFM images of $H(AB)_2$ and $H(AB)_{12}$ sequences in aqueous solutions. The $H(AB)_2$ sequence forms spherical aggregates with diameters of 6 ~ 10 nm, while the $H(AB)_{12}$ sequence forms slightly larger spherical aggregates with diameters of 15 ~ 20 nm. The two AFM height plots on the right provide quantitative values of the aggregate sizes measured along the red line in the AFM images. (b) Experimental FTIR-derived percentages of the protein secondary-structure contents for as synthesized $H(AB)_2$ and $H(AB)_{12}$ sequences, as well as the $H(AB)_{12}$ sequence after spinning. The sizes of $H(AB)_2$ and $H(AB)_{12}$ aggregates correlate directly with the ordered (β -sheet and helical) content. Only long sequences or polymer chains can form larger aggregates after shear flow that lead to film assembly. (c) DPD simulated median number of "a" beads per node (or aggregate size) after equilibration as a quantitative measure of the ordered contents, which correlates perfectly well with the FTIR results and is consistent with the AFM images. The lower and upper error bars are the 25% and 75% percentiles of all aggregate sizes, respectively.



Supplementary Figure 5 | (a) SEM images of $H(AB)_{12}$ in aqueous solutions at 2.5 mg/ml (top) and 1 mg/ml (bottom). Fibers (top) and nano-fibers (bottom) were observed for $H(AB)_{12}$. (b) Stiffness (Young's modulus) maps (top) and the corresponding stiffness distributions (bottom) of dried film samples of $H(AB)_{12}$ before spinning. The stiffness map is obtained using nanoindentation measurements over a 20 × 20 µm² squared region on the film with a 2 × 2 µm² resolution.



Supplementary Figure 6 | Series of SEM images showing the hierarchical structure of syringe spun silk fibre bundles using the $H(AB)_{12}$ sequence dissolved in HFIP. The spherical protein aggregates ($D \sim 60$ nm, bottom middle) are confirmed as the fundamental building block of the fibre.



Supplementary Figure 7 | Bright field microscopic images of the H(AB)₂ sequence after syringe spinning, showing disordered films when dissolved in both solvents.



Supplementary Figure 8 | Model of a multiply connected elastic network. Node 1 and node 2 are connected by total *N* springs with identical spring constant *k*. The left bridge has multiplicity *m* and the right bridge has multiplicity (N - m). The overall stiffness of the network shows a perfect analogy with a resistance network with identical connections.



Supplementary Figure 9 | Fourier Transform Infrared (FTIR) spectra and corresponding Fourier Self-Deconvolution (FSD) data for the $H(AB)_2$ sequence and the $H(AB)_{12}$ sequence before and after spun. The absorbance bands in the Amide I region are marked as random coil (R), β -sheets (B), α -helices (A), turns (T), and side chains (SC) in the FSD curve fitting plots.



Supplementary Figure 10 | Experimental setup and protocol for the syringe needle spinning of recombinant silk fibres.



Supplementary Figure 11 | Sample AFM nanoindentation results. Force vs. indentation depth curves for the original dried film (a) and the spun (b) fibre using the H(AB)₁₂ sequence.

Supplementary Table 1 | Amino acid sequences of the investigated silk-like protein blocks. Since poly(alanine) (A)_n and (GA)_n regions have been shown to form β -sheet structures in the fibre¹, we consider them as one logical block "A". The "H" block is a histidine-tag sequence of a pet30a(+) vector which possesses two enzymatic sites: enterokinase and thrombin cleavage sites.

Code	Silk-Like Protein Amino Acid Sequence	
"A" (hydrophobic), MW = 1247 Da	G A G A A A A A G G A G T S	
"B" (hydrophilic), MW = 1960 Da	Q G G Y G G L G S Q G S G R G G L G G Q T S	
"H" (hydrophilic), MW = 5239 Da	M H H H H H H S S G L V P R G S G M K E T A A A K F E R Q H M D S P D L G T D D D D K A M A A S	

	"w"	"a"	"b"
"w"	25	40	26
"a"	40	25	27
"b"	26	27	25

Supplementary Table 2 | Repulsive interaction parameter a_{ij} for the DPD potential.

Supplementary Discussion

Correlation between Protein Length, Network Percolation and Fibre Mechanics. Consider a protein composed by *N* units, each of them composed itself by n_a amorphous regions *A* of unit length *a* and n_b crystalline regions *B* of unit length *b*, namely β -sheets of length $n_b b$ in artificially spun or natural silk. The protein can be denoted as $(An_aBn_b)N$; in real spider silk $n_a = n_b = 1 \approx N/100$. The length of the protein is thus $L_N = (an_a + bn_b)N = L_1N$. An interaction can take place only between *B* regions of a same (self-interaction) protein or of different (cross-linked) proteins. The self-interaction is defined here as the number fraction s = n/N of β -sheets assembled together in the same crystal and protein after spinning. According to this, after spinning, the contour length of the protein becomes $l = L_1N(N - n)$ whereas the transversal size of the crystal is d = nc, where *c* is the separation distance between the β -sheets in the crystalline phase.

Denoting with ϕ the proteins content in the silk and with $i = \phi - \phi$ their geometrical overlapping fraction after spinning (an index of their interaction) with percolation theory we find $i = \phi + e^{-\phi} - 1$. At the percolation threshold $\phi = \phi_c$ and its critical value can be calculated numerically. An analytical estimation can be obtained invoking percolation theory; in particular, following Xia and Thorpe² and denoting by $\lambda = \frac{l}{d} + \frac{d}{l}$ the "protein slenderness", $\phi_c \approx -\ln \frac{1+4\lambda}{19+4\lambda}$.

The strength (a similar argument can be invoked for the Young's modulus) of the silk is thus expected to scale as $\sigma_s \approx \sigma_c (\phi - \phi_c)^{\gamma} \cos^k \vartheta$ where σ_c is the strength of the protein and $\vartheta = \sqrt{\langle \theta^2 \rangle}$, where ϑ is the protein orientation after spinning; according to rubber elasticity (in agreement with classical rules of mixture) we expect $\gamma \approx 1$ whereas assuming a discrete network $k \approx 1$ (for a continuum $k \approx 2$)³.

During spinning the proteins become more aligned for two main reasons: shear mixing and fibre dimension reduction. Denoting by $\mathcal{G}(R)$ the orientation after spinning at a fibre size R, we can calculate the orientation $\mathcal{G}(r)$ for a different fibre size r fixing the degree of mixing. Assuming the liquid crystal as incompressible we find $\tan \mathcal{G}(r) = (r/R)^{\omega} \tan \mathcal{G}(R)$ with $\omega = 2$; note that for constant volume under small elastic deformations, that is not the case of large plastic deformations that we have considered here, the Poisson's ratio is v = 1/2; the other limiting case of v = 0 denotes maximal compressibility and, for such a case, we find the same scaling but with the exponent $\omega = 1$). The strength thus assumes the form:

$$\sigma_{s} \approx \frac{(\phi - \phi_{c})^{\gamma}}{\left(1 + (r/R)^{2\omega} \tan^{2} \vartheta(R)\right)^{k/2}} \sigma_{c} \qquad \phi \ge \phi_{c} \qquad \sigma_{s} \approx 0 \quad \phi < \phi_{c}$$
(1)

with:

$$\phi_c \approx -\ln\frac{1+4\lambda}{19+4\lambda}, \quad \lambda = \frac{l}{d} + \frac{d}{l}, \quad \frac{l}{d} = \frac{L_1 N}{c} \left(\frac{N}{n} - 1\right), \quad L_1 = an_a + bn_b$$
(2)

Note that σ_c itself is a function of the protein length, e.g., according to Weibull's statistics, namely:

$$\sigma_{c}(N, n_{a}, n_{b}) \approx \sigma_{c}(N = n_{a} = n_{b} = 1) \cdot N^{-\frac{1}{m}} n_{a}^{-\frac{1}{m_{a}}} n_{b}^{-\frac{1}{m_{b}}}$$
(3)

where m, m_a, m_b are the related Weibull's moduli.

According to the model, for short protein lengths or small values of N, the strength of the chain increases but the interaction between the proteins decreases, and vice versa for long protein lengths or N. Thus an optimal value for the number N naturally emerges from the model; such optimal value for maximal strength is likely close to the experimental value observed in spider silk (the number N could also be limited by processability during spinning, this mechanism would have an effect similar to that of Weibull).

Furthermore, assuming the same Weibull's moduli, since *N* appears at the second power in λ whereas n_a, n_b appear at the first power, would imply a maximal strength minimizing the numbers n_a, n_b : this is observed in spider silk, for which $n_a = n_b = 1$. Note that a minimal value λ_c or content ϕ_c or units *N* naturally emerge from the model in order to have a non-vanishing strength; in the asymptotic limit of $\lambda >> 1$, for example, we find: $\lambda_c \approx 9/(2\phi)$ or $\phi_c \approx 9/(2\lambda)$. Vanishing strength for short proteins have been observed experimentally and numerically (**Fig. 7**).

Finally note that the asymptotic scaling of the strength is $\sigma_s \approx (r/R)^{-\omega k}$ with $\omega k = 1$ for a network of maximal compressibility, $\omega k = 2$ for an incompressible network or a continuum with maximal compressibility (that thus can be considered similar systems in this context) and $\omega k = 4$ for an incompressible continuum. Accordingly, for our protein network, we expect after spinning an intermediate scaling of $\omega k \approx 3/2$, very close to the experimental observations⁴.

Correlation between Network Conductance and Young's Modulus. To demonstrate the observed correlation between the network conductance and Young's modulus, we consider a multiply connected elastic network, established via total *N* bridges with identical spring constant *k* as shown in **Supplementary Fig. 8**. Node 1 and node 2 are connected by another node in the middle via spring bundle with *m* multiplicity and (N - m) multiplicity, respectively. The total stiffness between two nodes k_{12} can be written as $\left(\frac{1}{mk} + \frac{1}{(N-m)k}\right)^{-1} = \frac{(N-m)m}{N}k$. We can immediately realize that the coefficient $\frac{(N-m)m}{N}$ is the network conductance due to the analogy between an elastic network and a resistance network.

Thus, the network conductance not only captures the percolation of network but also the stiffness of the elastic network as demonstrated in **Fig. 7**, regardless of network topology. The Young's modulus of both isotropic homogeneous networks before shear and anisotropic inhomogeneous network after shear show strong a correlation with network conductance. In contrast, the total number of bridges *N* shows a direct proportionality with the Young's modulus of the network only before shear (**Fig. 7** (**b**)). When two nodes are connected by identical number of springs (that is, $m = \frac{N}{2}$), the overall stiffness k_{12} becomes $\frac{N}{4}k$, which is proportional to the total number of bridges *N*. This proportionality between stiffness and *N* corresponds to the prediction of the classical polymer theory, applicable here before spinning (limiting case for *m* being equals to N/2; in the condition verified before spinning, see **Fig. 7** (**b**)). Whereas, in general cases and both before and after spinning, and for different levels of

heterogeneity, we observe a proportionality between stiffness and conductance (N-m)m/N (see Fig. 7 (b)), which is hence identified as the key parameter for predictive design of biological silk fibers.

Supplementary Methods

General DPD Modelling Approach. To simulate the fibre formation process, we employed the dissipated particle dynamics (DPD)⁵, a mesoscale particle-based coarse-graining simulation method. DPD allows to access time and length scales that are far beyond the reach of ordinary molecular dynamics, but of high interest for polymers and large biomolecules. DPD is a representative mesoscopic computational model that has been widely applied to study the structural evolution of complex polymer solutions. Using the DPD method, we model silk fibres as polymeric soft matter, which is different from our previous bead-spring model that coarse-grains silk fibres into a triangular crystal lattice⁶. This new approach allows for more structural flexibility for the protein building-blocks of silk and is indeed suitable for subsequent modelling of the large structural evolution during the shear flow spinning process. We simulate the structural changes of the silk protein/polymer solutions during various processing steps consisting of: (a) equilibration of the aqueous polymer solution (right after the protein synthesis), (b) shearing of the polymer solution (to mimic the flow focusing condition in the microchannel⁴), and (c) stretching of the resulting polymer fibres (to mechanically test their robustness and stiffness). It is reasonable to describe the spinning process to be a pure shear flow because the shear strain is much higher than the elongational strain, as validated by computational fluid dynamics (CFD) simulations⁷. In this study, silk peptides and proteins are described as multiblock copolymer chains composed of hydrophobic "a" and hydrophilic "b" beads, each representing 3 amino acids in the "A" and "B" domains of the copolymer, respectively. The polymer chains are immersed in water in which every 9 water molecules are represented by one hydrophilic "w" bead. Note that the "H" domain is modelled using the same hydrophilic "b" beads as in the "B" domain as a reasonable approximation. A fixed 20% volume fraction of coarse-grained polymer beads is used in all cases to match the experimental spinning condition.

We model spider silk inspired peptides and proteins as a linear chain of two type of beads: i) beads of block A that are denoted with the lowercase letter "a", and ii) beads of block "B" denoted by the lowercase letter "b". The amino acid sequence of block "A" is "GAGAAAAAGGAGTS", mimicking the poly-alanine domain of the MaSp1 protein in the natural silk. On the other hand, the sequence of block "B" is "QGGYGGLGSQGSGRGGLGGQTS" which is inspired by the other MaSp1 domain with Gly-rich GGX repeats. Our model describes the properties of block "A" and "B" at a coarse-grained level and hence we omit the chemical details of different amino acids within the blocks. Key properties incorporated for block "A" are hydrophobicity and the ability to form hydrogen bonds with other members of "A" blocks. Block "B" is simplified as being hydrophilic. Other interactions are not taken into account for our model. We assemble the "A" and "B" blocks to peptides of various sequences to explore effects of various hydrophobic/hydrophilic ratio and chain length, with explicit water particles denoted by "w". The interaction between particles is short-ranged and nonsingular, allowing us to use a considerably larger time step compared to conventional MD simulations. Compressibility and solubility of particles are described by purely repulsive soft potential. Neighbouring particles in a polypeptide chain are interacted via a simple bead-spring model, and hydrogen bonds between "a" beads are modelled by a short-ranged modified harmonic potential.

In DPD, the time evolution of the particle positions are simulated according to Newton's equations of motion where the force acting on a particle adds up three pair-wise forces: the conservative force \vec{F}_{ij}^{C} , the dissipative force \vec{F}_{ij}^{D} and a random force \vec{F}_{ij}^{R} , giving

$$\vec{F}_{i} = \sum_{j \neq i} (\vec{F}_{ij}^{C} + \vec{F}_{ij}^{D} + \vec{F}_{ij}^{R})$$
(4)

where the sum contains only particles j within a certain cut-off radius R_c . The conservative force is given by

$$\vec{F}_{ij}^{C} = -a_{ij} \left(1 - \frac{|\vec{r}_{ij}|}{R_c} \right) \hat{r}_{ij}$$
(5)

The parameter a_{ij} determines the maximum repulsion between particles *i* and *j*, $\vec{r}_{ij} = \vec{r}_j - \vec{r}_i$ and \hat{r}_{ij} is a unit vector along \vec{r}_{ij} . The values of a_{ij} are fitted to reproduce the compressibility of the liquid and the solubility of various components by mapping into Flory-Huggins χ parameter^{5,8}. We added two more conservative forces \vec{F}_{HB}^{C} and \vec{F}_{PC}^{C} to account for the effects of hydrogen bonding and polymer chains, respectively. The details of those terms will be described in later sections.

The remaining two forces, the dissipative and the random force, acting as heat sink and source, respectively, are given by

$$\vec{F}_{ij}^D = -\gamma w^D (r_{ij}) (\hat{r}_{ij} \cdot \vec{v}_{ij}) \hat{r}_{ij}$$
⁽⁶⁾

$$\vec{F}_{ij}^R = \sigma w^R (r_{ij}) \theta_{ij} \hat{r}_{ij} \tag{7}$$

where w^D and w^R are *r*-dependent weight functions, that are set to zero at $r \ge R_c$, $v_{ij} = v_j - v_i$, and $\theta_{ij}(t)$ is a Gaussian-distributed randomly fluctuating variable with zero mean and unit variance. The random function is independent for each pair of particles. While one weight function can be chosen arbitrarily, it has been shown⁹ that for sampling a *NVT* ensemble the following relation must hold:

$$2k_B T \gamma w^D(r) = \sigma [w^R(r)]^2 \tag{8}$$

$$\sigma^2 = 2k_B T \gamma \tag{9}$$

This particular thermostat is special in that it conserves momentum and thus correctly describes hydrodynamics. As common in DPD simulations, we take $w^D(r) = \left(1 - \frac{r}{R_c}\right)^2$. The DPD cut-off R_c is taken as the characteristic length scale and $k_B T$ as the characteristic energy scale and the mass is also set to unity and hence, $R_c = k_B T = m = 1$. The friction parameter is set to $\gamma = 4.5$ following other publications^{10,11}. The simulation time is expressed in a natural time unit of $\tau = R_c \sqrt{\frac{m}{k_B T}}$ and time step of 0.03τ is used in the present study.

Coarse-graining Scheme and Time/Length Scales. We coarse grain nine water molecules into one bead. The molecular volume of water is 30 Å³, so that one bead represents a volume of 270 Å³. Following the convention, we chose the beads of different phases, i.e., "a" and "b", to be of equal volume with water bead. By comparing the amino acid residue volumes¹² in the sequence, we find that the alanine residue volume is close to the mean volume of all amino acid residues in blocks "A" and "B", and is therefore chosen as a reference volume. The alanine residue volume of 86 Å³ is about a third of the single bead volume of 270 Å³, giving the coarse-graining level of three amino acid residues per bead. As presented in **Supplementary Table 1**, the given peptide sequences are lumped into 5 "a" beads for one A-block and 7 "b" beads for one B-block. The hydrophilic hexahistidine tag is introduced for facile purification in experiments, and is modelled as 16 "b" beads here for simplicity.

The number density of the simulation is chosen to be $\rho R_c^3 = 3$. Taking into account that one bead represents a volume of 270 Å³, we have $R_c = 9.321$ Å. At 300 K, $k_BT = 4.14 \times 10^{-21}$ J = 41.4 pN · Å. *m* is the mass of 9 water molecules, i.e., $m = 2.692 \times 10^{-25}$ kg. Combining these values, we obtain the intrinsic time scale $\tau_{int} = R_c \sqrt{\frac{m}{k_B T}} = 7.52$ ps.

However, because of the coarse-graining, we lose track of the physical unit of time. To gauge the time unit, the long-time diffusion constant of water is matched. Following the study of Groot 2001^{13} , the physical time unit can be written as follows, $\tau_{physical} = \frac{N_m D_{sim} R_c^2}{D_{water}}$ where N_m is the number of water molecules in a bead and D_{water} is the self diffusion constant of water¹⁴, 2.43×10^{-5} cm²/s. With the noise parameter $\gamma = 4.5$ and $a_{ww} = 25$, we obtain the self diffusion constant of water beads $D_{sim} = \frac{0.23R_c^2}{\tau}$. This leads to the physical time scale of $\tau_{physical} = 0.75$ ns, and a time step of $\Delta t = 0.03\tau = 0.0224$ ns which is about 5 orders of magnitude larger than the conventional MD time step.

Interaction Parameters. (1) Repulsive interaction parameters a_{ij} : The magnitude of the repulsive conservative force parameters $a_{ij} = a_{ii} + [\Delta a]_{ij}$ are determined to represent the compressibility and solubility of the system. To match the compressibility of water^{5,8}, the repulsive interaction between two beads of the same species, including water, hydrophobic, and hydrophilic beads is chosen as $a_{ii} = a_{ww} = a_{aa} = a_{bb} = 25$. The remaining parameters $[\Delta a]_{ij}$ can be chosen to represent hydrophobic and hydrophilic interactions of "a" and "b" beads with water, by mapping into the phenomenological Flory-Huggins parameter $\chi^{5,8}$. A distinct value of χ is required for amino acid residues, but no such experiments are found in the literature to the best of our knowledge. Even though the distinct χ values are available for all amino acids in the sequence, we cannot follow the rigorous mapping procedure due to complex chemical details of each amino acid. Instead, we chose to take parameters that can qualitatively capture the overall behaviour such as formation of stable micelle from diblock copolymer, and miscibility between "A" and "B" blocks^{15,16}. We have chosen values from existing studies^{10,11}, where the stable micelle formation are observed. All a_{ij} values are presented in **Supplementary Table 2**.

(2) Peptide chain bead spring model: The force-extension behaviour of a single spider silk peptide has been described by the worm like chain (WLC) model with persistence length $\lambda_p = 4.0$ Å from atomic microscopic experiments¹⁷, and the elastic stiffness over full extension has been calculated by full atomistic simulations^{1,18-20}. For simplicity, we model each peptide chain with a simple bead-spring model where equilibrium segment length is *a* and the force between neighbouring beads are given by $-k_{seg}(r-a)$, so called extensible freely jointed chain (EFJC). The force-extension curve for EFJC can be obtained analytically as follows,

$$f = \frac{k_B T}{a} L^{-1} \left(\frac{r}{L_{tot}}\right) \tag{10}$$

where *f* is the stretch force, *r* is the end-to-end distance, k_B is Boltzmann constant, and *T* is the absolute temperature. When there are *n* segments in the chain, L_{tot} is given by $na + \frac{nf}{k_{seg}}$, i.e., contour length plus the amount of extension by applied force *f*. The inverse Langevin function L^{-1} is defined as $\frac{r}{L_{tot}} = \operatorname{coth} \beta - \frac{1}{\beta} = L(\beta)$ and $\beta = L^{-1} \left(\frac{r}{L_{tot}}\right)$. Because the full force-extension of WLC or extensible WLC cannot be fully captured by our simple bead-spring model, we attempt to correctly

model two asymptotic regimes, small extension regime near r = 0 and the elastic extension regime near the full extension.

Near r = 0, it is known that $f^{FJC} = \frac{3k_BT}{na^2}r$ and $f^{WLC} = \frac{3k_BT}{2\lambda_p L_{cont}}r$ where L_{cont} is the contour length of the chain. The small extension response can be matched by making the slope of f - r curve identical. Noting that the fully extended trans-peptide bond is 3.8 Å, we have the full extension length $l = 3 \times 3.8 = 11.2$ Å between two neighboring beads in the chain. Conventionally, the contour length na of the FJC is chosen to be the physical contour length nl and a is set to be $2\lambda_p$, which makes the FJC much softer than WLC at high extension regime. Instead, by choosing $a = \sqrt{2\lambda_p l} = 9.55$ Å = $1.025 R_c$, we obtain the identical small extension response between FJC and WLC, as well as moderately good match at high extension regime (**Supplementary Fig. 1 (a)**). Close to the full extension, the slope of the EFJC force extension curve approaches to $\frac{k_{seg}}{n}$ due to finite rigidity of each bond, which can be interpreted as the stretch of covalent bonds. Full atomistic simulation studies have shown that the effective stiffness of seven 54 amino acid long spider silk repeats to be $103.8 \frac{pN}{A}$. Noting that 54 amino acid peptide chain has 18 segments in our coarse-graining level, $k_{seg} = 18 \times \frac{103.8}{7} = 268.2 \frac{pN}{A} = 118.5 \frac{k_BT}{R_c^2}$. Overall, our EFJC model describes the WLC force extension curve very well, as shown in **Supplementary Fig. 1 (a)**.

(3) Hydrogen bonding potential: Each amino acid residue forms two hydrogen bonds with amino acids in the nearby peptide, and the hydrogen bonding energy obtained from atomistic simulation is $2.83 \frac{\text{kcal}}{\text{mol}} = 4.75 k_B T$ at T = 300K. Thus, the cohesive energy of each coarse-grained bead is required to be $6 \times 4.75 = 28.5 k_B T$.

We do not consider the orientation dependence of hydrogen bond, but simply overlay a shortranged modified harmonic potential to the DPD potential with a cutoff distance R_c . The explicit form of the overlaid potential is

$$U^{HB}(r) = \begin{cases} -E_0 \frac{\left(R_c^2 - r^2\right)^2 \left(R_c^2 + 2r^2 - 3r_0^2\right)}{\left(R_c^2 - r_0^2\right)^3} \text{ for } r > r_0 \\ \frac{1}{2} k_{HB} (r - r_0)^2 - E_0 & \text{ for } r \le r_0 \end{cases}$$
(11)

where the spring constant is chosen to match the second order derivative of the potential around $r = r_0$, so that $k_{HB} = \frac{24r_0^2 E_0}{(R_c^2 - r_0^2)^2}$, as depicted in **Supplementary Fig. 1** (b). The functional form converges smoothly to zero at $r = R_c$ and the force F^{HB} is computed from negative derivative of U^{HB} .

Because the lowest energy configuration is face-centred-cubic (FCC) crystal for an isotropic potential, we set the equilibrium distance between the beads is set to be 0.778 R_c to match the DPD density of $\rho R_c^3 = 3$. Note that the cohesive energy of an "a" bead corresponds to 10 times the broken bond energy, due to two physical bonds with two neighbouring amino acids in the same chain. Thus, the individual bond energy is chosen to be $\frac{28.5}{10} = 2.85 k_B T$. To have the bond energy of hybrid DPD plus HB potential to be $2.85k_B T$ at distance $0.778 R_c$ as depicted in Fig 3, we iteratively determine $r_0 = 0.756 R_c$ and $E_0 = 3.53 k_B T$. The equilibrium distance *a* between neighbouring "a" beads in the chain is chosen to be $0.778 R_c$ to match the equilibrium distance of hybrid potential. Thus, the WLC force-extension curve matches only with the B block of the chain. However, using a different equilibrium distance for "a"-"a" bond would affect the assembly process and mechanical property of

the fiber negligibly, because "a" beads form aggregated crystals for the most of the time and would not play a significant role except the onset of failure.

Modelling Shear Flow. The laminar flow in microfluidic channel⁴ is modelled by achieving Couette flow condition in the simulation cell. The Lees-Edwards boundary conditions were applied to generate the shear flow²¹ such that the same shear rate was applied to all materials in the system. Specifically, we deform the box with a constant engineering strain rate $\dot{\gamma}_{xy}$, by constantly increasing the tilt of the simulation box. The tilt in the x-direction continues until the shear strain of 0.5 is reached, then the box flips to the negative 0.5 shear strain while keeping the real coordinates and velocities of particles. A continuous shear flow is generated by repeating this procedure. When a particle crosses a periodic boundary along y axis, a delta is added (or subtracted) to its velocity that is equal to the difference of velocities between the low and high boundary, i.e., $\Delta \vec{v} = L_y \dot{\gamma}_{xy} \hat{x}$. This process generates the velocity profile $v_x(y)$ that linearly varies from $-\frac{1}{2}L_y \dot{\gamma}_{xy}$ at y = 0 to $\frac{1}{2}L_y \dot{\gamma}_{xy}$ at $y = L_y$, as presented in **Supplementary Fig. 2 (a)**.

The steady-state shear flow and translational velocity along x axis induced by our method are not compatible with conventional thermostats such as Nose-Hoover thermostat and Langevin thermostat where temperature is regulated by feedback algorithms based on the absolute velocity of each particle. However, DPD thermostat relies on the relative velocity between a pair of particles within short cutoff distance R_c , and temperature is regulated effectively with small errors. The periodic boundary along y has exceptionally high relative velocity due to velocity remapping boundary, which creates deviation from the perfect Couette flow condition around y = 0 and $y = L_y$. However, the volume fraction of the area is relatively small and overall effect on the thermostat is negligible, as shown in **Supplementary Fig. 2 (b)**.

Experimental SEM, AFM and FTIR Analysis. Under SEM, the HAB₃ sequence forms perforated films with a pore size of ~ 200 nm (Supplementary Fig. 3 (a), top), but small spherical aggregates are also observed for the HAB₃ sequence with diameters ranging between 50 and 200 nm (Supplementary Fig. 3 (a), bottom). In contrast, the HA₃B sequence forms much larger microspheres with diameters ranging between 0.5 and 5 µm (Supplementary Fig. 3 (c)). The H(AB)₂ sequence forms condensed films composed of intermediate-sized spherical aggregates with diameters ranging between 0.2 and 0.6 μm (Supplementary Fig. 3 (b)). This trend that block copolymers possessing larger hydrophobichydrophilic domain ratios form larger aggregates is in good agreement with other theoretical¹¹ and experimental²² studies on self-assembly of block copolymers in aqueous solutions. This trend is also confirmed by our previous Fourier Transform Infrared (FTIR) Spectroscopy measurements¹⁵, which further provides the percentages of various protein secondary-structure contents for the peptide aggregates (centre around the β -sheet crystals) after Fourier Self-Deconvolution (FSD) of the FTIR spectra (Supplementary Fig. 3 (d)). Both helical and disordered contents exhibit minor changes among the above three peptide cases, while the percentage of the β -sheet content varies a lot and correlates perfectly well with the "A"-"B" domain ratio. This morphological correlation is also well captured in our DPD simulations in which the number of "a" beads per aggregate (referred to as "node" here) measures the amount of the ordered (β -sheet and helical) contents in the aggregate (Supplementary Fig. 3 (e)).

Under AFM, the H(AB)₂ sequence forms spherical aggregates with diameters of $6 \sim 10$ nm, while the H(AB)₁₂ sequence forms slightly larger spherical aggregates with diameters of $15 \sim 20$ nm

(Supplementary Fig. 4 (a)). FTIR-derived percentages of protein secondary-structure contents show similar β -sheet contents for H(AB)₂ and H(AB)₁₂ sequences, but the longer H(AB)₁₂ sequence exhibits greatly enlarged β -sheet contents (or aggregate size) after the spinning process (modelled by the shear flow here) (Supplementary Fig. 4 (b)). This morphological change is also well captured in our DPD simulated ordered contents of H(AB)₂ (before shear flow) and H(AB)₁₂ (both before and after shear flow) (Supplementary Fig. 4 (c)).

It is noteworthy that for HFIP-dissolved $H(AB)_{12}$ solutions, the dried and the rehydrated fibres exhibit similar averaged stiffness values (**Fig. 6 (f)**), with a slight broadening in stiffness distribution of the rehydrated case. However, for $H(AB)_{12}$ dissolved in aqueous LiBr solutions, the resulting dried fibre is 10 times stiffer than the rehydrated one (**Fig. 6 (f)**), which might be due to the dramatic fiber structural change from supercontraction²³. The ultrahigh stiffness value of 8 ± 4 GPa for the dried fibres when using water as the solvent suggests that silk proteins self-assemble much better in water (e.g., to facilitate intermolecular hydrogen bonds) than in organic solvents such as HFIP to yield stiffer fibres.

Supplementary References

- 1 Keten, S. & Buehler, M. J. Nanostructure and molecular mechanics of spider dragline silk protein assemblies. *Journal of the Royal Society Interface* **7**, 1709-1721 (2010).
- 2 Xia, W. & Thorpe, M. F. Percolation Properties of Random Ellipses. *Phys Rev A* **38**, 2650-2656 (1988).
- 3 Pugno, N. M. The design of self-collapsed super-strong nanotube bundles. *J Mech Phys Solids* **58**, 1397-1410 (2010).
- 4 Kinahan, M. E. *et al.* Tunable silk: using microfluidics to fabricate silk fibers with controllable properties. *Biomacromolecules* **12**, 1504-1511 (2011).
- 5 Groot, R. D. & Warren, P. B. Dissipative particle dynamics: Bridging the gap between atomistic and mesoscopic simulation. *J Chem Phys* **107**, 4423-4435 (1997).
- 6 Teule, F. *et al.* A protocol for the production of recombinant spider silk-like proteins for artificial fiber spinning. *Nat Protoc* **4**, 341-355 (2009).
- 7 Breslauer, D. N., Lee, L. P. & Muller, S. J. Simulation of flow in the silk gland. *Biomacromolecules* **10**, 49-57 (2008).
- 8 Maiti, A. & McGrother, S. Bead-bead interaction parameters in dissipative particle dynamics: relation to bead-size, solubility parameter, and surface tension. *J. Chem. Phys.* **120**, 1594 (2004).
- 9 Espanol, P. & Warren, P. Statistical-mechanics of dissipative particle dynamics. *Europhysics Letters* **30**, 191-196 (1995).
- 10 Spaeth, J. R., Kevrekidis, I. G. & Panagiotopoulos, A. Z. A Comparison of Implicit- and Explicit-Solvent Simulations of Self-Assembly in Block Copolymer and Solute Systems. *J. Chem. Phys.* **134**, 164902 (2011).
- Sheng, Y. J., Wang, T. Y., Chen, W. M. & Tsao, H. K. A-B diblock copolymer micelles:
 Effects of soluble-block length and component compatibility. *Journal of Physical Chemistry B* 111, 10938-10945 (2007).
- 12 Zamyatnin, A. A. Amino-Acid, Peptide, and Protein Volume in Solution. *Annual Review of Biophysics and Bioengineering* **13**, 145-165 (1984).
- 13 Groot, R. D. & Rabone, K. L. Mesoscopic simulation of cell membrane damage, morphology change and rupture by nonionic surfactants. *Biophys. J.* **81**, 725-736 (2001).
- Partington, S., Hudson, R. F. & Bagnall, K. W. Self-Diffusion of Aliphatic Alcohols. *Nature* 169, 583-584 (1952).
- 15 Huang, W. W., Krishnaji, S., Hu, X., Kaplan, D. L. & Cebe, P. Heat capacity of spider silk-like block copolymers. *Macromolecules* **44**, 5299-5309 (2011).
- 16 Krishnaji, S. T. *et al.* Sequence–structure–property relationships of recombinant spider silk proteins: integration of biopolymer design, processing, and modeling. *Advanced Functional Materials* 23, 241-253 (2012).
- 17 Oroudjev, E. *et al.* Segmented nanofibers of spider dragline silk: Atomic force microscopy and single-molecule force spectroscopy. *Proc. Natl. Acad. Sci. U.S.A.* **99**, 6460-6465 (2002).
- 18 Keten, S. & Buehler, M. J. Geometric confinement governs the rupture strength of H-bond assemblies at a critical length scale. *Nano. Lett.* **8**, 743-748 (2008).
- 19 Nova, A., Keten, S., Pugno, N. M., Redaelli, A. & Buehler, M. J. Molecular and Nanostructural mechanism of deformation, strength, and toughness of spider silk fibrils. *Nano Letters* **10**, 2626-2634 (2010).
- 20 Keten, S. & Buehler, M. J. Atomistic model of the spider silk nanostructure. *Applied Physics Letters* **96**, 153701 (2010).

- 21 Lees, A. W. & Edwards, S. F. The computer study of transport processes under extreme conditions. *Journal of Physics C: Solid State Physics* **5**, 1921 (1972).
- 22 Mai, Y. Y. & Eisenberg, A. Self-assembly of block copolymers. *Chem Soc Rev* **41**, 5969-5985 (2012).
- 23 Liu, Y., Shao, Z. Z. & Vollrath, F. Relationships between supercontraction and mechanical properties of spider silk. *Nat Mater* **4**, 901-905 (2005).